

# Size Measurement of Dry, Granular Drilling Fluid Particulates

API TECHNICAL REPORT 13TR3  
FIRST EDITION, OCTOBER 2018



AMERICAN PETROLEUM INSTITUTE

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, NW, Washington, DC 20005.

*Copyright © 2018 American Petroleum Institute*

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this recommended practice are as follows:

- the term “shall” denotes a minimum requirement in order to conform to the recommended practice;
- the term “should” denotes a recommendation or that which is advised but not required in order to conform to the recommended practice;
- the term “may” is used to express permission or a provision that is optional; and
- the term “can” is used to express possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, DC 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 1220 L Street, NW, Washington, DC 20005. Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).



## Contents

	Page	
1	Scope . . . . .	1
2	Terms, Definitions, and Abbreviations . . . . .	1
2.1	General Terms . . . . .	1
2.2	Abbreviations . . . . .	4
3	Characteristics of Granular Lost Circulation Materials . . . . .	5
4	Particle Size Distributions (PSD) . . . . .	5
5	Sampling . . . . .	5
6	Methods of Sizing Drilling Fluid Particulates . . . . .	6
6.1	General . . . . .	6
6.2	PSA Techniques . . . . .	6
6.3	Usage Applications of PSA Techniques-Drilling and Completion Fluids Industry . . . . .	9
7	Size Analysis Technique Recommendations Based on Particle Size . . . . .	10
8	Comparison of PSA Methods for Fine, Medium, Coarse, and Extremely Coarse Materials . . . . .	11
8.1	General . . . . .	11
9	Reporting of Results . . . . .	15
10	Recommendations for Particulate Size Reporting of Granular Materials Used in Drilling Fluids . . . . .	16
10.1	Reader Header . . . . .	16
10.2	Particle Size Distribution (PSD) . . . . .	17
10.3	Examples of PSD Reports . . . . .	18
	Bibliography . . . . .	24
<b>Figures</b>		
1	Optimum Size Range of Some PSA Techniques . . . . .	9
2	Particle Size Parameters for API Barite . . . . .	12
3	Particle Size Parameters for Fine CaCO <sub>3</sub> . . . . .	12
4	Particle Size Parameters for Medium CaCO <sub>3</sub> . . . . .	13
5	Particle Size Parameters for Coarse CaCO <sub>3</sub> . . . . .	14
6	Particle Size Parameters for Extra Coarse CaCO <sub>3</sub> . . . . .	14
7	Particle Size Parameters for 6-Mesh Al <sub>2</sub> O <sub>3</sub> . . . . .	15
8	Graphic Laser Diffraction PSD of a Barite Composite Sample . . . . .	19
9	Graphic Laser Diffraction PSD of a Drilling Fluid System . . . . .	19
10	Graphic Laser Diffraction PSD of a Blended Product . . . . .	20
11	Graphic Laser Diffraction PSD of a Drilling Fluid System . . . . .	20
12	Dry Sieve Analysis: Cumulative Mass Passing Opening Sieve Size . . . . .	21
13	Dry Sieve Analysis: Cumulative Mass Passing Opening Sieve Size . . . . .	21
14	Dry Image Analysis: Blended CaCO <sub>3</sub> , PSD, and Particle Aspect Ratio . . . . .	22
15	Dry Image Analysis: Blended CaCO <sub>3</sub> , Semi-log Plot of Differential Vol % vs Size . . . . .	22
16	Dry Image Analysis: Blended CaCO <sub>3</sub> , Frame Capture . . . . .	23
17	Dry Image Analysis: CaCO <sub>3</sub> Nominal $d_{50} = 250 \mu\text{m}$ . . . . .	23
<b>Tables</b>		
1	Sizing Method Recommendations for Granular Materials . . . . .	10
2	Sizing Method Recommendations for Anisometric Materials (Aspect ratio > 6:1) . . . . .	11
3	Example Cumulative Particle Size Distribution by Volume % vs Size . . . . .	18
4	Example Cut Point Data . . . . .	18



# Size Measurement of Dry, Granular Drilling Fluid Particulates

## 1 Scope

This report is intended to serve as a guide for the selection of appropriate techniques to determine the particle size distribution (PSD) of relatively large dry solid additives for drilling fluids, especially lost circulation materials (LCMs). Detailed procedures for the utilization of any specific PSD method are not included. The technician should refer to and be guided by the measurement equipment manufacturer's instructions. The particulates range in size from approximately one micron to as much as several millimeters in diameter, and are considered "granular" in shape, i.e. relatively isometric (of similar length, width, and height). The recommendations in this technical report generally are not applicable to the measurement of the PSD of nonisometric (high aspect ratio) materials such as fibers or flakes.

## 2 Terms, Definitions, and Abbreviations

### 2.1 General Terms

#### 2.1.1

##### **anisometric**

Having two or more axes that are significantly different from each other

NOTE The opposite is "isometric"; see 2.1.6.

#### 2.1.2

##### **aspect ratio**

A numeric expression of the relative length, width, and height (or thickness) of a particle as a ratio.

NOTE 1 Aspect ratio provides information on the shape of a particulate.

NOTE 2 The preferred format of the expression is with the largest axis in the primary position, the second-largest axis in the secondary position, and the smallest axis in the third (last) position. (example: 3.5 : 2.5 : 1) An alternative format for the aspect ratio is a value equivalent to the largest axis divided by the smallest axis (example: 3.5, only one number is provided).

#### 2.1.3

##### **axes**

##### **axis (singular)**

The three principal measured dimensions of a discrete particle, measured orthogonally (at 90-degree angles) from one another, commonly known as length, width, and height.

#### 2.1.4

##### **differential plot**

In a particle size distribution, a chart showing the percentile of a population (by count, mass, or volume) of particles within defined size ranges.

NOTE This is usually displayed as a linear or semi-log histogram plot of % versus size.

#### 2.1.5

##### **granule**

##### **granular (adjective)**

A particle that has axial dimensions (i.e. aspect ratio) that are near to isometric.

NOTE Distinguished from flake or fibrous materials in that they do not have significantly flattened or elongated dimensions.