

# **S-N Fatigue Design Guidelines and Test Data for Low-alloy Steel Bolts**

API TECHNICAL REPORT 21TR2  
FIRST EDITION, MARCH 2022



American  
Petroleum  
Institute

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be used. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001-5571.

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, “can” denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001, [standards@api.org](mailto:standards@api.org).



## Contents

	Page
1	Scope..... 1
2	Normative References ..... 1
3	Terms, Definitions, Abbreviations, and Symbols ..... 1
3.1	Terms and Definitions ..... 1
3.2	Acronyms, Abbreviations, and Symbols ..... 1
4	Bolting Fatigue Analysis Design Guidelines ..... 2
4.1	Fatigue Sensitivity Criteria for Bolting ..... 2
4.2	Bolting S-N Fatigue Analysis Procedure ..... 2
5	Full-Scale Fatigue Test Data for Bolting..... 3
5.1	Bolting Materials ..... 3
5.2	S-N Fatigue Testing ..... 6
6	Conclusions ..... 20
	Bibliography ..... 22

## Figures

1	Thread Root Profiles for 1-in. Bolts from the Two Heats (Manufacturers) ..... 11
2	1-in. Bolt, 1-D-M-U-7 Showing an Imperfection ..... 12
3	S-N Fatigue Curve for 1-in. Bolts in Ambient Air ..... 13
4	S-N Fatigue Curve for 2-in. Bolts in Ambient Air ..... 14
5	S-N Fatigue Curve for 3-in. Bolts in Ambient Air ..... 15
6	Comparison of Mean-2SD S-N Fatigue Curves for the 1-in., 2-in. and 3-in. Bolts Tested in Ambient Air ... 16
7	S-N fatigue Curves for 1-in. Bolts in Ambient Air and SW+CP ..... 17
8	S-N Fatigue Curves for 2-in. Bolts in Ambient Air and SW+CP ..... 18
9	S-N Fatigue Curves for 3-in. Bolts in Ambient Air and SW+CP ..... 19
10	Comparison of Mean-2SD S-N Fatigue Curves for the 1-in., 2-in., and 3-in. Bolts Tested in SW+CP ..... 20

## Tables

1	Bolts and Nuts used for Phase 1 of FSF Testing of LAS Bolting ..... 3
2	Bolt and Nut Heat Numbers, Reduction Ratios, and Chemical Composition ..... 4
3	Heat Treatment Details of the Bolts and Nuts Prior to Machining..... 4
4	Mechanical Properties of the Bolts and Nuts ..... 5
5	Load Levels Applied to Bolts (SMYS = 105ksi [725 MPa]) ..... 6
6	Bolt Dimensions and Calculated Nominal Root Area for Each Bolt Size ..... 6
7	Applied Stress Ranges and Corresponding Loads for Each Bolt Size ..... 7
8	S-N Fatigue Test Results for 1-in. Bolts in Ambient Air (Dry) and SW+CP (Wet) Conditions ..... 8
9	S-N Fatigue Test Results for 2-in. Bolts in Ambient Air (Dry) and SW+CP (Wet) Conditions ..... 9
10	S-N Fatigue Test Results for 3-in. Bolts in Ambient Air (Dry) and SW+CP (Wet) Conditions ..... 9
11	Fatigue Test Knock-down Factors for SW+CP/Ambient Air ..... 20



## Introduction

The requirements for bolting fatigue assessment were a charge of the API CSOEM Multi-Segment Task Group on Bolting Failures. Due to documented subsea bolting failures defined in the BSEE QC-FIT Evaluation of Connector and Bolt Failures, the charge of the sub task group TGR-13 was the following:

*“Guidance should be issued by API on when and how to perform fatigue sensitivity analysis on bolting.”*

API CSOEM Bolting Report for TGR-13 and TGR-14 was issued. It defined the design guidelines and provided recommendations for performing a full-scale fatigue testing on bolting. Upon further approval, full-scale fatigue testing was performed.

The following guidelines are provided for both design verification fatigue analysis and corresponding full-scale fatigue testing that was performed.

Design verification analysis for fatigue assessment of bolting requires an evaluation for S-N or fatigue crack growth rate. The S-N fatigue evaluation can be based on either the stress concentrations of the thread profile, which will need stress amplification factor (SAF) or stress concentration factor (SCF) and smooth tensile bar S-N testing, or minimum root diameter stress without thread profile, which will need full-scale bolt fatigue tests. The basis of this document is the S-N approach using full-scale fatigue testing. The purpose of the full-scale bolt fatigue testing was to obtain S-N fatigue life for bolts manufactured to meet API 20E BSL-3 and the requirements of API 17D loading condition. The fatigue testing was based on alternating axial stresses in the bolt with a defined preload. The preload was applied with the load frame to a value of  $2/3 \cdot YS$  based on the cross-section at the root radius of the thread. The defined bolt lengths represent API flange by flange connection conservative bolt lengths for a given bolt size. The bolt-to-nut thread engagement met the requirements of API 6A. Each bolt tested had two bolt/nut connections where the failure of the first connection was defined as the fatigue life.

The objective of the test program was to provide S-N fatigue curves for bolts that are preloaded to API Series 17 standards and are subjected to a range of alternating axial stresses. The preload and alternating stress ranges were defined based on the cross-sectional area at the root radius of the threads. The test program evaluated bolt size effects and environments of air and saltwater with cathodic protection (CP).



# S-N Fatigue Design Guidelines and Test Data for Low Alloy Steel Bolts

## 1 Scope

The scope of the test program was to obtain bolting material fatigue data required to perform design verification analysis of fatigue-sensitive bolts to assure accurate design life estimation. The bolting fatigue testing program provided S-N fatigue curves for three alternating stress ranges in air and saltwater with CP and for bolt sizes of 1 in., 2 in. (Grade L7), and 3 in. (Grade L43).

The results of these S-N fatigue tests allow the bolting design to be assessed for S-N fatigue through structural analysis using the nominal root area stresses in the bolt, avoiding the need to define stress and load concentrations in the bolt root radius of engaged threads.

The design guidelines and the fatigue data provided in the document are intended to be used for bolting with unified national thread with root radius (UNR) specifications of ASME B1.1 class 2A/2B.

## 2 Normative References

There are no referenced documents that are indispensable for the application of this document.

## 3 Terms, Definitions, Abbreviations, and Symbols

### 3.1 Terms and Definitions

#### 3.1.1

#### high-stress range fatigue cycles

#### HFC

Tested fatigue cycles to failure for a high-stress range or high force condition applied.

#### 3.1.2

#### low-stress range fatigue cycles

#### LFC

Tested fatigue cycles to failure for a low-stress range or low force condition applied.

#### 3.1.3

#### medium-stress range fatigue cycles

#### MFC

Tested fatigue cycles to failure for a medium-stress range or medium force condition applied.

#### 3.1.4

#### stress range

The difference between the maximum stress and minimum stress being applied.

### 3.2 Acronyms, Abbreviations, and Symbols

CP	cathodic protection
EF	electric furnace
HFC	high-stress range fatigue cycles
FSF	full-scale fatigue
LFC	low-stress range fatigue cycles
MFC	medium-stress range fatigue cycles
MPS	manufacturing process specification