



CGA P-56—2022
CRYOGENIC VAPORIZATION
SYSTEMS—PREVENTION OF
BRITTLE FRACTURE OF
EQUIPMENT AND PIPING

THIRD EDITION

PREFACE

As part of a program of harmonization of industry standards, the Compressed Gas Association (CGA) has issued CGA P-56, *Cryogenic Vaporization System—Prevention of Brittle Fracture of Equipment and Piping*, jointly produced by members of the International Harmonization Council and originally published by the European Industrial Gases Association (EIGA) as EIGA Doc 133, *Cryogenic Vaporisation Systems – Prevention of Brittle Fracture of Equipment and Piping*.

This publication is intended as an international harmonized standard for the worldwide use and application of all members of the Asia Industrial Gases Association (AIGA), Compressed Gas Association (CGA), European Industrial Gases Association (EIGA), and Japan Industrial and Medical Gases Association (JIMGA). Each association's technical content is identical, except for regional regulatory requirements and minor changes in formatting and spelling.

PLEASE NOTE:

The information contained in this document was obtained from sources believed to be reliable and is based on technical information and experience currently available from members of the Compressed Gas Association, Inc. and others. However, the Association or its members, jointly or severally, make no guarantee of the results and assume no liability or responsibility in connection with the information or suggestions herein contained. Moreover, it should not be assumed that every acceptable commodity grade, test or safety procedure or method, precaution, equipment or device is contained within, or that abnormal or unusual circumstances may not warrant or suggest further requirements or additional procedure.

This document is subject to periodic review, and users are cautioned to obtain the latest edition. The Association invites comments and suggestions for consideration. In connection with such review, any such comments or suggestions will be fully reviewed by the Association after giving the party, upon request, a reasonable opportunity to be heard. Proposed changes may be submitted via the Internet at our web site, www.cganet.com.

This document should not be confused with federal, state, provincial, or municipal specifications or regulations; insurance requirements; or national safety codes. While the Association recommends reference to or use of this document by government agencies and others, this document is purely voluntary and not binding.

A listing of all publications, audiovisual programs, safety and technical bulletins, and safety posters is available via the Internet at our website at www.cganet.com. For more information contact CGA at Phone: 703-788-2700, ext. 799. E-mail: customerservice@cganet.com

Work Item 18-029
Atmospheric Gases and Equipment Committee

NOTE—Technical changes from the previous edition are underlined.

THIRD EDITION: 2022
SECOND EDITION: 2014
FIRST EDITION: 2006

© – Reproduced with permission from, the European Industrial Gases Association. All rights reserved.

Contents	Page
1 Introduction.....	1
2 Scope and purpose	1
3 Definitions.....	2
4 Types of vaporizers	4
4.1 High thermal ballast vaporizers	4
4.2 Low thermal ballast vaporizers	5
5 Causes and consequences of low temperature	5
5.1 Causes of low temperature.....	5
5.2 Consequences of low temperature.....	6
6 Design philosophy	7
6.1 Inherent safety	7
6.2 Risk assessment	8
6.3 Reliability of customer supply	9
7 Ranking of hazards	9
7.1 Pressure volume energy.....	10
7.2 Hazard of fluid	10
7.3 Likelihood of low temperature.....	10
7.4 Operating pattern.....	10
8 Safe design criteria.....	11
8.1 Vaporizer outlet materials.....	11
8.2 Natural draft ambient air-heated vaporizers	12
8.3 Independent layers of protection	12
8.4 Shutoff devices and valves.....	13
8.5 Throttling valves	13
8.6 Temperature sensing devices	13
8.7 Vaporization system flow capacity.....	14
8.8 Low thermal ballast vaporizers.....	14
8.9 Buffer vessels and location.....	14
8.10 Different vaporizers in parallel.....	16
9 Considerations for low temperature protection.....	16
9.1 Uninterruptible supply system	16
9.2 Interruptible supply requirements	18
9.3 IEC 61511.....	19
10 Solutions.....	19
10.1 General considerations for low temperature protection systems.....	19
10.2 Response to alarms.....	19
10.3 Recommended solutions for specific situations.....	20
11 Operation.....	24
11.1 Consumption monitoring.....	24
11.2 Manual defrosting	25
12 Periodic inspection, calibration, and testing	25
12.1 Periodic inspection	25
12.2 Periodic calibration and testing.....	26

13	Training for gas company personnel	26
14	Customer awareness	27
14.1	Customer agreement.....	27
14.2	Customer training and information	27
15	References	28

Tables

Table 1	—Causes of low temperature.....	5
Table 2	—Pressure volume energy classification	10
Table 3	—Fluid hazard classification	11
Table 4	—Classification of likelihood of low temperature occurrence.....	11
Table 5	—Classification of service type	11
Table 6	—Recommended LTPS selection: PV severity levels P0, P1, P2, and P3.....	21

Figures

Figure 1	—Relationship between impact energy and temperature for carbon and austenitic stainless steels	6
Figure 2	—Buffer installation for continuous service.....	14
Figure 3	—Other buffer installation possible for continuous service	15
Figure 4	—Buffer installation preferred for back-up service.....	15
Figure 5	—Other buffer installation possible for back-up service.....	16

1 Introduction

Cryogenic (or cold) fluids can be inadvertently admitted to process piping and equipment due to the malfunctioning of cryogenic liquid vaporization systems, which can result in catastrophic failure due to brittle fracture. When certain metals, typically carbon steels, become cold they undergo changes in their structure, which makes them less ductile, i.e., they become brittle. Other metals such as stainless steels, aluminum, brass, and copper do not exhibit this ductile/brittle transition and remain ductile at low temperatures. This publication has been written to identify the hazards associated with cryogenic liquid vaporization systems and to recommend the safeguards to be taken.

2 Scope and purpose

This publication applies to cryogenic liquid supply systems, located either on a customer site or a production site, where cryogenic liquid is vaporized and is then supplied either as the primary or secondary source of gaseous product. This publication is limited to the prevention of brittle fracture in piping and associated equipment installed downstream of the vaporization system.

The secondary source of supply can be a back-up supply to a production plant when the production plant trips or is shut down, a supplementary supply to meet customer demand where it exceeds the capacity of the production plant (peak shaving), or as a back-up supply at a customer site (for example, a healthcare facility).

The safeguard principles presented in this publication apply to any process fluid supply system where the temperature of the cryogenic liquid source is less than the minimum temperature rating of the piping and/or associated equipment downstream of the vaporizer.

Examples include:

- nitrogen;
- oxygen;
- argon;
- helium;
- hydrogen;
- natural gas;
- carbon monoxide;
- methane; and
- ethylene.

Carbon dioxide and nitrous oxide are excluded from the scope of this publication; however, the principles of this publication may be applied.

The supply systems work by vaporizing cryogenic liquid, typically in response to decreasing pipeline pressure.

Supply systems are made up of the following:

- liquid supply from either a low pressure tank and pump arrangement or directly from a high pressure tank;
- vaporization system that could be a natural draft ambient air-heated type or one that uses an external energy source for example, steam, hot water, electricity, direct fired;
- interconnecting liquid and outlet gas piping, valves, and fittings up to the battery limit; and
- low temperature protection system (LTPS) as detailed in this publication.

Although this publication does not cover the following situations, the techniques listed may be considered for cold embrittlement prevention:

- Air separation and other cryogenic processes with columns, separators, or tanks in which a gas stream from a sump is normally supplied through downstream heat exchange equipment, or liquefaction units where a cryogenic fluid can exit through warm-end process piping during a shutdown or upset scenario. Cryogenic processes are assumed to have their own LTPS;
- Piping systems within which a fluid is expanded across a valve or restriction with the resultant temperature being less than the ductile-to-brittle-transition-temperature (DBTT) for the piping system; and
- Vessels that are depressurized rapidly: as work is done in a vessel by a gas expanding as it is discharged out of the valve, the temperature inside the vessel and the vessel wall can be lowered.

This publication recommends safe practice for the design of new cryogenic vaporizer systems. For existing systems, a risk assessment shall be undertaken to establish if any modifications are required. The principles developed in this publication can be used for this purpose.

3 Definitions

For the purpose of this publication, the following definitions apply.

3.1 Publication terminology

3.1.1 Shall

Indicates that the procedure is mandatory. It is used wherever the criterion for conformance to specific recommendations allows no deviation.

3.1.2 Should

Indicates that a procedure is recommended.

3.1.3 May

Indicates that the procedure is optional.

3.1.4 Will

Is used only to indicate the future, not a degree of requirement.

3.1.5 Can

Indicates a possibility or ability.

3.2 Technical definitions

3.2.1 Battery limit

Physical point where the rights and responsibilities of custody of the gaseous product transfers from the supplier to the customer.

3.2.2 Brittle fracture

Failure caused by a crack that propagates rapidly through the material. A brittle material has little resistance to failure once the elastic limit has been reached.

NOTE—Pressurized equipment subject to such a failure leads to a sudden and violent energy release, the projection of fragments, and the release of a fluid that can be oxidizing, flammable, toxic, etc.

3.2.3 Ductile

Property of a metal that allows it to elongate, with a rapid increase in local stresses, prior to failing.

3.2.4 End use point

Physical location where gaseous product is consumed by the customer.