



CGA C-17—2022
METHODS TO AVOID AND
DETECT INTERNAL
CORROSION OF GAS
CYLINDERS AND TUBES

THIRD EDITION

PREFACE

As part of a program of harmonization of industry standards, the Compressed Gas Association (CGA) has issued CGA C-17, *Methods to Avoid and Detect Internal Corrosion of Gas Cylinders and Tubes*, jointly produced by members of the International Harmonization Council and originally published by the European Industrial Gases Association (EIGA) as EIGA Doc 62, *Methods to avoid and detect internal corrosion of gas cylinders and tubes*.

This publication is intended as an international harmonized standard for the worldwide use and application of all members of the Asia Industrial Gases Association (AIGA), Compressed Gas Association (CGA), European Industrial Gases Association (EIGA), and Japan Industrial and Medical Gases Association (JIMGA). Each association's technical content is identical, except for regional regulatory requirements and minor changes in formatting and spelling.

PLEASE NOTE:

The information contained in this document was obtained from sources believed to be reliable and is based on technical information and experience currently available from members of the Compressed Gas Association, Inc. and others. However, the Association or its members, jointly or severally, make no guarantee of the results and assume no liability or responsibility in connection with the information or suggestions herein contained. Moreover, it should not be assumed that every acceptable commodity grade, test or safety procedure or method, precaution, equipment or device is contained within, or that abnormal or unusual circumstances may not warrant or suggest further requirements or additional procedure.

This document is subject to periodic review, and users are cautioned to obtain the latest edition. The Association invites comments and suggestions for consideration. In connection with such review, any such comments or suggestions will be fully reviewed by the Association after giving the party, upon request, a reasonable opportunity to be heard. Proposed changes may be submitted via the Internet at our web site, www.cganet.com.

This document should not be confused with federal, state, provincial, or municipal specifications or regulations; insurance requirements; or national safety codes. While the Association recommends reference to or use of this document by government agencies and others, this document is purely voluntary and not binding unless adopted by reference in regulations.

A listing of all publications, audiovisual programs, safety and technical bulletins, and safety posters is available via the Internet at our website at www.cganet.com. For more information contact CGA at Phone: 703-788-2700, ext. 799. E-mail: customerservice@cganet.com.

Work Item 18-054
Cylinder Specifications Committee

NOTE—Technical changes from the previous edition are underlined.

THIRD EDITION: 2022
SECOND EDITION: 2014
FIRST EDITION: 2008

© Reproduced with permission from, the European Industrial Gases Association. All rights reserved.

Contents	Page
1 Introduction.....	1
2 Scope and purpose	1
3 Definitions.....	1
4 Corrosion.....	2
5 Sources of moisture contamination	2
5.1 Water from manufacturer’s hydraulic test.....	2
5.2 Water from product/filling operation.....	2
5.3 Water backflow during use	2
5.4 Water ingress	2
5.5 Water from periodic inspection of cylinders.....	3
6 Avoidance of cylinder corrosion	3
6.1 Material selection and cylinder design.....	3
6.2 Avoidance of water ingress	4
6.3 Moisture detection methods	5
6.4 Corrosion detection methods.....	6
7 Guidance for moisture acceptance levels	6
8 Recommendations/Conclusions	6
8.1 Using a residual pressure valve with a nonreturn function	6
8.2 Cylinders without residual pressure valves	6
8.3 Use of aluminum alloy cylinders	6
9 References	7
10 Additional references.....	7

1 Introduction

There are a number of reasons for a cylinder or a tube to fail. These reasons can include but are not limited to, abuse, misuse, manufacturing flaws, and internal corrosion. A number of gases can react with moisture to produce corrosive media that could react with the cylinder or tube material and lead to a cylinder or tube failure. The number of incidents resulting from internal corrosion is relatively small compared to the number of cylinders and tubes in service because the industry follows procedures to reduce moisture in cylinders and tubes.

2 Scope and purpose

This publication provides guidance to help prevent and detect internal corrosion of compressed gas cylinders and tubes. It applies to gas cylinders, bundles of cylinders, and tubes including installations at customer sites.

NOTE—Unless noted by exception, the use of the word “cylinder” in this publication refers to both cylinders and tubes.

The main emphasis of this publication focuses on steel cylinders containing oxygen/oxygen mixtures including compressed air and carbon dioxide/carbon dioxide mixtures in the presence of moisture. Certain aspects of this publication can also apply to other gases that can react in the presence of moisture such as hydrogen chloride.

3 Definitions

For the purpose of this publication, the following definitions apply.

3.1 Publication terminology

3.1.1 Shall

Indicates that the procedure is mandatory. It is used wherever the criterion for conformance to specific recommendations allows no deviation.

3.1.2 Should

Indicates that a procedure is recommended.

3.1.3 May

Indicates that the procedure is optional.

3.1.4 Will

Is used only to indicate the future, not a degree of requirement.

3.1.5 Can

Indicates a possibility or ability.

3.2 Technical definitions

3.2.1 Bundle of cylinders

Portable assembly that consists of a frame and two or more cylinders, each of a capacity up to 150 L and with a combined capacity of not more than 3000 L, or 1000 L in the case of toxic gases, connected to a manifold by cylinder valves or fittings such that the cylinders are filled, transported, and emptied without disassembly.

3.2.2 Corrosion

Reaction of the cylinder material with certain aqueous media (for example, carbonic acid formed from carbon dioxide and water).

3.2.3 Corrosive gas

Gas in a cylinder that will interact with the cylinder material in an oxidizing manner in the presence of moisture.