

Manufacture of Structural Steel Forgings for Primary Offshore Applications

API SPECIFICATION 2SF
FIRST EDITION, AUGUST 2013

REAFFIRMED, SEPTEMBER 2020



Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Copyright © 2013 American Petroleum Institute

Foreword

The verbal forms used to express the provisions in this specification are as follows:

- the term “shall” denotes a minimum requirement in order to conform to the specification;
- the term “should” denotes a recommendation or that which is advised but not required in order to conform to the specification;
- the term “may” is used to express permission or a provision that is optional;
- the term “can” is used to express possibility or capability.

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001, standards@api.org.

Contents

Page

1	Scope	1
2	Normative References	1
3	Terms, Definitions, Abbreviations, and Acronyms	2
3.1	Terms and Definitions	2
3.2	Abbreviations and Acronyms	3
4	Manufacturing and Quality Requirements	4
4.1	Quality Plan (QP) and Manufacturing Procedure Specification (MPS)	4
4.2	Manufacturer, Facility, and Subcontractor Approval	5
4.3	Lowest Anticipated Service Temperature (LAST)	5
4.4	Service Categories	5
4.5	Critical Sections	5
4.6	Forging Specifications	5
4.7	Traceability	5
4.8	Information Supplied to the Forging Manufacturer	6
4.9	Documents Requiring Approval by Purchaser and Contractor	6
4.10	Preproduction Meeting	7
4.11	Post-job Production Histograms	7
4.12	Certificates	7
5	Manufacturing Process and Chemical Composition	7
5.1	Steel Making and Refining Practice	7
5.2	Chemical Composition	8
5.3	Forging Process	10
5.4	Repair Welding	10
6	Heat Treatment	11
6.1	Heat Treatment Process Control Requirements	11
6.2	Quenching	11
6.3	Heat Treatment Furnace Records/Charts, Temperatures, and Cycle Times	11
7	Qualification Test Sample (QTS)	11
7.1	Forgings Represented by QTS	11
7.2	QTS Dimensional Requirements	11
7.3	Heat Treatment of QTSs	12
8	Mechanical Properties and Tests	12
8.1	Tensile Tests	12
8.2	Hardness Tests	13
8.3	CVN Tests	14
8.4	Retesting	15
9	Weldability of Service Category B Forgings	15
9.1	SCB Welding Prequalification	15
9.2	Tensile Tests	16
9.3	CVN Testing	16
9.4	Macrosection Microhardness Survey	17

Contents

	Page
10 NDE of Forgings	17
10.1 Ultrasonic Testing (UT)	17
10.2 Magnetic Particle Examination (MT)	18
10.3 Visual Examination (VT)	20
10.4 Documentation of NDE Results	20
11 Dimensional Inspection	20
12 Material Test Report	20
Annex A (normative) Supplementary Requirements	21
Annex B (informative) API Monogram Program	23
Bibliography	26
Tables	
1 Industry Standard Chemical Composition Specifications	8
2 Elemental Limits	9
3 A707-modified Chemical Composition	10
4 Tensile Properties and Hardness Requirements	13
5 CVN Absorbed Energy Requirement—Service Category A and B	14
6 CVN Absorbed Energy Requirements—Service Category C	15

Introduction

This specification is based on the experience acquired during the design, construction, operation, and maintenance of offshore processing units and facilities, as supplemented with the experience of operating companies with topsides, fixed platforms, floating structures (e.g. TLPs, spars, etc.), and their tendons and risers. Forgings in these applications tend to be limited production components, with relatively few replications, and receive more intense scrutiny than routine mass production runs.

Where appropriate this specification is based on, or reference is made to, international, regional, national, and industry standards.

This is a manufacturing specification for the forging itself. It is anticipated that geometric design for both service requirements and forging feasibility will have been agreed collectively between the contractor, manufacturer, and purchaser before this specification is invoked. Attendant issues regarding system reliability, geometric design, incorporation into the overall construction, operation, and maintenance are not addressed in this specification. Those electing to use this specification as a reference for their needed level of performance quality should carefully consider all of these attendant issues.

Manufacture of Structural Steel Forgings for Primary Offshore Applications

1 Scope

Forgings manufactured to this specification are intended for use in the fabrication of offshore structures, marine risers, TLP tendons and pipelines, or other system components intended for application on permanent offshore structures. This specification defines the minimum requirements for manufacture, testing, and inspection of carbon and low-alloy steel forgings, including extrusions and heavy-wall seamless tubular product, grades 345 N/mm² to 586 N/mm² (50 ksi to 85 ksi) for use in primary steel applications.

Service categories A, B, and C (SCA, SCB, and SCC) reflect forging geometry and method of incorporation into the overall system, rather than levels of criticality. They may also be designated by the user (purchaser) as described in 4.4 to reflect moderately different but standardized levels of performance.

2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Recommended Practice 2Z, *Preproduction Qualification for Steel Plates for Offshore Structures*, Fourth Edition

ASME Boiler and Pressure Vessel Code (BPVC) ¹, Section V: *Nondestructive Examination; Article 9: Visual Examination*, 2007

ASME Boiler and Pressure Vessel Code (BPVC), Section VIII: *Rules for Construction of Pressure Vessels*, 2007

ASTM A275 ², *Standard Practice for Magnetic Particle Examination of Steel Forgings*

ASTM A370, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

ASTM A751, *Standard Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products*

ASTM A788, *Standard Specification for Steel Forgings, General Requirements*

ASTM E10, *Standard Test Method for Brinell Hardness of Metallic Materials*

ASTM E23, *Standard Test Methods for Notched Bar Impact Testing of Metallic Materials*

ASTM E110, *Standard Test Method for Indentation Hardness of Metallic Materials by Portable Hardness Testers*

ASTM E2375, *Standard Practice for Ultrasonic Testing of Wrought Products*

ASTM E384, *Standard Test Method for Knoop and Vickers Hardness of Materials*

ASTM E709, *Standard Guide for Magnetic Particle Testing*

ASTM E1444-12, *Standard Practice for Magnetic Particle Testing*

¹ ASME International, 3 Park Avenue, New York, New York 10016-5990, www.asme.org.

² ASTM International, 100 Barr Harbor Drive, West Conshohocken, Pennsylvania 19428, www.astm.org.