

# **Design, Materials, Fabrication, Operation, and Inspection Guidelines for Corrosion Control in Hydroprocessing Reactor Effluent Air Cooler (REAC) Systems**

API RECOMMENDED PRACTICE 932-B  
SECOND EDITION, MARCH 2012

ERRATA, JANUARY 2014



AMERICAN PETROLEUM INSTITUTE



# **Design, Materials, Fabrication, Operation, and Inspection Guidelines for Corrosion Control in Hydroprocessing Reactor Effluent Air Cooler (REAC) Systems**

**Downstream Segment**

API RECOMMENDED PRACTICE 932-B  
SECOND EDITION, MARCH 2012

ERRATA, JANUARY 2014



AMERICAN PETROLEUM INSTITUTE

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Users of this Recommended Practice should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein.

API is not undertaking to meet the duties of employers, manufacturers, or suppliers to warn and properly train and equip their employees, and others exposed, concerning health and safety risks and precautions, nor undertaking their obligations to comply with authorities having jurisdiction.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, NW, Washington, DC 20005.

*Copyright © 2012 American Petroleum Institute*

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the specification.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, DC 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 1220 L Street, NW, Washington, DC 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).



# Contents

Page

1	Scope	1
2	Normative References	2
2.1	Codes and Standards	2
2.2	Other References	3
3	Terms, Definitions, and Acronyms	4
3.1	Terms and Definitions	4
3.2	Acronyms	5
4	Background of REAC Corrosion	5
4.1	History of Reactor Effluent System Corrosion Surveys	5
4.2	Typical Hydroprocessing Units	6
4.3	Effluent Separation Designs	8
4.4	REAC System Corrosion	8
5	Strategies to Promote System Reliability	11
5.1	General	11
5.2	Material Selection and Design	12
5.3	Establishing an Operating Envelope (Integrity Operating Window)	12
5.4	Inspection Plans	13
6	Process Variables Affecting Corrosion	13
6.1	Ammonium Bisulfide Concentration	13
6.2	Process Conditions at the Water Dew Point	13
6.3	Fluid Velocities	14
6.4	Hydrogen Sulfide (H <sub>2</sub> S) Partial Pressure	15
6.5	Flow Regime	16
6.6	Chlorides	16
6.7	Other Process Variables	17
6.8	Wash Water	17
6.9	Corrosion Inhibitors	20
6.10	Air Cooler Fan Operations	20
6.11	Process Monitoring	20
7	Materials of Construction	21
7.1	General	21
7.2	Material Selection Criteria	22
8	Equipment Specific Design Considerations	25
8.1	Fin Fan Air Coolers	25
8.2	Shell-and-Tube Trim Coolers	27
8.3	Cold High-Pressure Separator (CHPS)	27
8.4	Heat Exchanger or Air Cooler Upstream of REAC	28
8.5	Piping & Valves	28
9	Inspection of the REAC System	32
9.1	General	32
9.2	Reactor Effluent Air Coolers	32
9.3	Piping	35
9.4	Pressure Vessels—Separators, Heat Exchanger Shells	36
10	Limitations and Recent Improvements in the Industry Knowledge Base	36

<b>10.1 Experience</b> .....	<b>36</b>
<b>10.2 Recent Joint Industry Research</b> .....	<b>37</b>
<b>Annex A (normative) Process Calculations and Estimates</b> .....	<b>39</b>
<b>Bibliography</b> .....	<b>43</b>

#### Figures

<b>1 Example Hydrotreating Unit Process Flow Diagram</b> .....	<b>7</b>
<b>2 Example Hydrocracking Unit Process Flow Diagram</b> .....	<b>7</b>
<b>3 Example Process Scheme with a CHPS</b> .....	<b>9</b>
<b>4 Example Process Scheme with a CHPS and CLPS</b> .....	<b>9</b>
<b>5 Example Process Scheme with Two Separators, a HHPS and CHPS</b> .....	<b>10</b>
<b>6 Example Process Scheme with Four Separators</b> .....	<b>10</b>
<b>7 Isocorrosion Curves for Carbon Steel at Various NH<sub>4</sub>HS Concentrations and Velocities through Small Orifice (0.15 in.) Coupons</b> .....	<b>14</b>
<b>8 Curves Showing Effect of H<sub>2</sub>S Partial Pressure on Corrosion of Carbon Steel</b> .....	<b>15</b>
<b>9 Relative Alloy Performance in Aqueous NH<sub>4</sub>HS Service</b> .....	<b>25</b>
<b>10 Illustration of a Balanced and Unbalanced Inlet Piping Configuration</b> .....	<b>31</b>
<b>11 Cross Section of Internal Surface of Failed REAC Outlet Nozzle</b> .....	<b>33</b>
<b>12 Erosion-Corrosion of Carbon Steel Piping Elbow</b> .....	<b>35</b>
<b>A.1 Estimating NH<sub>4</sub>HS Deposition Temperature from Process Stream Composition</b> .....	<b>40</b>
<b>A.2 Estimating NH<sub>4</sub>Cl Deposition Temperature from Process Stream Composition</b> .....	<b>41</b>

#### Tables

<b>1 Keys to REAC Systems 2</b> .....	<b>18</b>
<b>2 Quality Parameters of Injected Wash Water</b> .....	<b>21</b>
<b>3 Guidelines for Monitoring Process Variables</b> .....	<b>23</b>
<b>4 Referenced Material Compositions</b> .....	<b>42</b>
<b>A.1 FC Value</b> .....	<b>42</b>

# Design, Materials, Fabrication, Operation, and Inspection Guidelines for Corrosion Control in Hydroprocessing Reactor Effluent Air Cooler (REAC) Systems

## 1 Scope

This recommended practice (RP) provides guidance to engineering and plant personnel on equipment and piping design, material selection, fabrication, operation, and inspection practices to manage corrosion and fouling in the wet sections of hydroprocessing reactor effluent systems. The reactor effluent system includes all equipment and piping between the exchanger upstream of the wash water injection point and the cold, low-pressure separator (CLPS). The majority of these systems have an air cooler, however, some systems utilize only shell and tube heat exchangers. Reactor effluent systems are prone to fouling and corrosion by ammonium bisulfide ( $\text{NH}_4\text{HS}$ ) and ammonium chloride ( $\text{NH}_4\text{Cl}$ ) salts.

An understanding of all variables impacting corrosion and fouling in these systems is necessary to improve the reliability, safety, and environmental impact associated with them. Past attempts to define generic optimum equipment design and acceptable operating variables to minimize fouling and corrosion have had limited success due to the interdependence of the variables. Corrosion can occur at high rates and be extremely localized, making it difficult to inspect for deterioration and to accurately predict remaining life of equipment and piping. Within the refining industry, continuing equipment replacements, unplanned outages, and catastrophic incidents illustrate the current need to better understand the corrosion characteristics and provide guidance on all factors that can impact fouling and corrosion.

This RP is applicable to process streams in which  $\text{NH}_4\text{Cl}$  and  $\text{NH}_4\text{HS}$  salts can form and deposit in equipment and piping or dissolve in water to form aqueous solutions of these salts. Included in this practice are:

- details of deterioration mechanisms;
- methods to assess and monitor the corrosivity of systems;
- details on materials selection, design and fabrication of equipment for new and revamped processes;
- considerations in equipment repairs; and
- details of an inspection plan.

Table 1 lists key issues to REAC system performance and section reference for more detail.

Materials and corrosion specialists should be consulted for additional unit-specific interpretation and application of this document. This is especially important since new proprietary research is underway which challenges several previously held beliefs about  $\text{NH}_4\text{HS}$  corrosion in the reactor effluent system. Each facility needs to establish its own safe operating envelope to assure satisfactory service. This RP helps to identify key variables necessary for monitoring and establishing the operating envelope.

Other equipment downstream of the REAC can also deteriorate from these ammonium salts. These include the recycle gas, sour gas and the  $\text{H}_2\text{S}$  stripper and product fractionator overhead systems. Although these are beyond the scope of this document, plant personnel should be alert to these other locations where ammonium salt fouling and corrosion can occur.

Since the first edition of API 932-B was published in July 2004, findings from a recent joint industry sponsored research program contributed important new data on  $\text{NH}_4\text{HS}$  corrosion relevant to these systems. While not all the data are in the public domain, recent publications have highlighted key data which are incorporated into this current edition of API 932-B.