

# Welding of Pipelines and Related Facilities

## Pipeline Segment

API STANDARD 1104  
TWENTIETH EDITION, OCTOBER 2005

ERRATA/ADDENDUM, JULY 2004  
ERRATA 2, DECEMBER 2008

REAFFIRMED, APRIL 2010



AMERICAN PETROLEUM INSTITUTE

## SPECIAL NOTES

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

*All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.*

## FOREWORD

07 | The bar notations in the margins identify parts of this standard that have been changed from the previous API edition. While efforts have been made to ensure the accuracy of the notations, the user of this standard is responsible for recognizing any differences between this and the previous edition.

This standard was prepared by a formulating committee that included representatives of the American Petroleum Institute, the American Gas Association, the Pipe Line Contractors Association, the American Welding Society, and the American Society for Nondestructive Testing, as well as representatives of pipe manufacturers and individuals associated with related industries.

The purpose of this standard is to present methods for the production of high-quality welds through the use of qualified welders using approved welding procedures, materials, and equipment. Its purpose is also to present inspection methods to ensure the proper analysis of welding quality through the use of qualified technicians and approved methods and equipment. It applies to both new construction and in-service welding.

The use of this standard is entirely voluntary and is intended to apply to welding of piping used in the compression, pumping, and transmission of crude petroleum, petroleum products, fuel gases, carbon dioxide, and nitrogen and, where applicable, to distribution systems.

This standard represents the combined efforts of many engineers who are responsible for the design, construction, and operation of oil and gas pipelines, and the committee appreciatively acknowledges their wholehearted and valuable assistance.

From time to time, revisions of this standard will be necessary to keep current with technological developments. The committee is always anxious to improve this standard and will give full consideration to all comments received.

An appeal of any API standards action by an interested party shall be directed to the API.

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards and Publications Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).



# CONTENTS

	Page
1 GENERAL.....	1
1.1 Scope .....	1
2 REFERENCED PUBLICATIONS.....	1
3 DEFINITION OF TERMS .....	2
3.1 General.....	2
3.2 Definitions .....	2
4 SPECIFICATIONS.....	2
4.1 Equipment .....	2
4.2 Materials .....	3
5 QUALIFICATION OF WELDING PROCEDURES FOR WELDS CONTAINING FILLER-METAL ADDITIVES.....	3
5.1 Procedure Qualification .....	3
5.2 Record .....	3
5.3 Procedure Specification .....	3
5.4 Essential Variables.....	4
5.5 Welding of Test Joints-Butt Welds .....	7
5.6 Testing of Welded Joints-Butt Welds .....	7
5.7 Welding of Test Joints-Fillet Welds.....	9
5.8 Testing of Welded Joints-Fillet Welds.....	9
6 QUALIFICATION OF WELDERS .....	10
6.1 General.....	10
6.2 Single Qualification.....	10
6.3 Multiple Qualification .....	14
6.4 Visual Examination .....	17
6.5 Destructive Testing .....	17
6.6 Radiography Butt-welds Only.....	19
6.7 Retesting.....	19
6.8 Records.....	19
7 DESIGN AND PREPARATION OF A JOINT FOR PRODUCTION WELDING... ..	19
7.1 General .....	19
7.2 Alignment .....	19
7.3 Use of Lineup Clamp for Butt-welds .....	19
7.4 Bevel .....	20
7.5 Weather Conditions .....	20
7.6 Clearance .....	20
7.7 Cleaning Between Beads.....	20
7.8 Position Welding .....	20
7.9 Roll Welding .....	20
7.10 Identification of Welds.....	20
7.11 Pre-and Post-Heat Treatment.....	20
8 INSPECTION AND TESTING OF PRODUCTION WELDS.....	21
8.1 Rights of Inspection.....	21

	Page
8.2	Methods of Inspection . . . . . 21
8.3	Qualification of Inspection Personnel . . . . . 21
8.4	Certification of Nondestructive Testing Personnel. . . . . 21
9	ACCEPTANCE STANDARDS FOR NONDESTRUCTIVE TESTING . . . . . 21
9.1	General . . . . . 21
9.2	Rights of Rejection . . . . . 21
9.3	Radiographic Testing . . . . . 21
9.4	Magnetic Particle Testing . . . . . 27
9.5	Liquid Penetrant Testing . . . . . 27
9.6	Ultrasonic Testing . . . . . 28
9.7	Visual Acceptance Standards for Undercutting . . . . . 29
10	REPAIR AND REMOVAL OF DEFECTS . . . . . 29
10.1	Authorization for Repair . . . . . 29
10.2	Repair Procedure . . . . . 29
10.3	Acceptance Criteria . . . . . 29
10.4	Supervision. . . . . 30
10.5	Welder . . . . . 30
11	PROCEDURES FOR NONDESTRUCTIVE TESTING . . . . . 30
11.1	Radiographic Test Methods . . . . . 30
11.2	Magnetic Particle Test Method . . . . . 33
11.3	Liquid Penetrant Test Method . . . . . 33
11.4	Ultrasonic Test Methods . . . . . 33
12	MECHANIZED WELDING WITH FILLER METAL ADDITIONS . . . . . 37
12.1	Acceptable Processes . . . . . 37
12.2	Procedure Qualification . . . . . 37
12.3	Record . . . . . 37
12.4	Procedure Specification . . . . . 37
12.5	Essential Variables . . . . . 38
12.6	Qualification of Welding Equipment and Operators. . . . . 39
12.7	Records of Qualified Operators. . . . . 40
12.8	Inspection And Testing of Production Welds . . . . . 40
12.9	Acceptance Standards for Nondestructive Testing . . . . . 40
12.10	Repair and Removal of Defects. . . . . 40
12.11	Radiographic Testing. . . . . 40
13	AUTOMATIC WELDING WITHOUT FILLER-METAL ADDITIONS . . . . . 40
13.1	Acceptable Processes. . . . . 40
13.2	Procedure Qualification . . . . . 40
13.3	Record . . . . . 41
13.4	Procedure Specification . . . . . 41
13.5	Essential Variables . . . . . 41
13.6	Qualification of Equipment and Operators . . . . . 42
13.7	Records of Qualified Operators. . . . . 42
13.8	Quality Assurance of Production Welds . . . . . 43
13.9	Acceptance Standards for Nondestructive Testing . . . . . 46
13.10	Repair and Removal of Defects. . . . . 46
13.11	Radiographic Procedure. . . . . 46

	Page
APPENDIX A ALTERNATIVE ACCEPTANCE STANDARDS FOR GIRTH WELDS . . . . .	47
A.1 General . . . . .	47
A.2 Stress Analysis . . . . .	47
A.3 Welding Procedure . . . . .	49
A.4 Qualification of Welders . . . . .	52
A.5 Inspection and Acceptable Limits . . . . .	52
A.6 Record . . . . .	59
A.7 Repairs . . . . .	59
A.8 Nomenclature . . . . .	59
APPENDIX B IN-SERVICE WELDING . . . . .	61
B.1 General . . . . .	61
B.2 Qualification of In-service Welding Procedures . . . . .	61
B.3 In-service Welder Qualification . . . . .	63
B.4 Suggested In-service Welding Practices . . . . .	64
B.5 Inspection and Testing of In-service Welds . . . . .	64
B.6 Standards of Acceptability: Nondestructive Testing (Including Visual) . . . . .	65
B.7 Repair and Removal of Defects . . . . .	65
Figures	
1 Sample Procedure Specification Form . . . . .	5
2 Sample Coupon Test Report . . . . .	6
3 Location of Test Butt-weld Specimens for Procedure Qualification Test . . . . .	11
4 Tensile-strength Test Specimen . . . . .	12
5 Nick-break Test Specimen . . . . .	12
6 Root- and Face-bend Test Specimen: Wall Thicknesses Less Than or Equal to 0.500 in. (12.7 mm) . . . . .	13
7 Side-bend Test Specimen: Wall Thicknesses Greater than 0.500 in. (12.7 mm) . . . . .	13
8 Dimensioning of Imperfections in Exposed Weld Surfaces . . . . .	14
9 Jig for Guided-bend Tests . . . . .	15
10 Location of Nick-break Test Specimens: Fillet-weld Procedure and Welder Qualification Test Welds . . . . .	16
11 Location of Nick-break Test Specimens: Fillet-weld Procedure and Welder Qualification Test Welds, Including Size-to-size Branch-connection Welder Qualification Test . . . . .	16
12 Location of Test Butt-weld Specimens for Welder Qualification Test . . . . .	18
13 Inadequate Penetration Without High-Low (IP) . . . . .	22
14 Inadequate Penetration Due to High-low (IPD) . . . . .	24
15 Inadequate Cross Penetration (ICP) . . . . .	24
16 Incomplete Fusion at Root of Bead or Top of Joint (IF) . . . . .	24
17 Incomplete Fusion Due to Cold Lap (IFD) . . . . .	24
18 Internal Concavity (IC) . . . . .	24
19 Maximum Distribution of Gas Pockets: Wall Thicknesses Less Than or Equal to 0.500 in. (12.7 mm) . . . . .	25
20 Maximum Distribution of Gas Pockets: Wall Thicknesses Greater Than 0.500 in. (12.7 mm) . . . . .	26
21A Reference Block for Manual UT . . . . .	35
21B Establishing Distance, Refracted Angle, and Velocity . . . . .	36
21C Transfer Procedure . . . . .	36
22 Location of Test Butt-weld Specimens for Flash-weld Procedure Qualification Test: Outside Diameter Greater Than 18 in. (457 mm) but Less Than or Equal to 24 in. (610 mm) . . . . .	42

	Page		
23	Location of Test Butt-weld Specimens for Flash-weld Procedure Qualification Test: Outside Diameter Greater Than 24 in. (610 mm) but Less Than or Equal to 30 in. (762 mm) . . . . .	43	
24	Location of Test Butt-weld Specimens for Flash-weld Procedure Qualification Test: Outside Diameter Greater Than 30 in. (762 mm) . . . . .	44	
25	Two inch Nick-break Test Specimen . . . . .	45	
A-1	Top View (Width in Circumferential Direction) of the Tensile Test Specimen. . .	50	07
A-2	Charpy Specimen and V-Notch Location for the HAZ Impact Testing. . . . .	50	
A-3	Location of CTOD Test Specimens . . . . .	51	
A-4	Machine Objective for CTOD Test Specimen with Respect to Pipe Wall. . . . .	51	
A-5	Location of Notch for Weld-Metal Specimen . . . . .	52	
A-6	Location of Notch for Heat-Affected Zone Specimen. . . . .	52	
A-7	Option 1 Imperfection Limits for $CTOD \geq 0.010$ in. (0.25mm). . . . .	54	
A-8	Option 1 Imperfection Limits for $0.004$ in. (0.10mm) $\leq CTOD < 0.0010$ in. (0.25 mm) . . . . .	54	
A-9	Allowable Imperfection Size Curves Before and After Height Adjustment. . . . .	55	
A-10	Schematic Overview of the Option 2 Procedure . . . . .	56	
A-11	Criteria for Evaluation of Imperfection Interaction . . . . .	60	
B-1	Examples of Typical Temper-bead Deposition Sequences . . . . .	62	
B-2	Suggested Procedure and Welder Qualification Test Assembly . . . . .	65	
B-3	Location of Test Specimens—In-Service Welding Procedure Qualification Test . . . . .	66	
B-4	Macro Test Specimen—In-service Welds . . . . .	67	
B-5	Face-bend Test Specimen . . . . .	67	
B-6	Reinforcing Pad . . . . .	68	
B-7	Reinforcing Saddle . . . . .	68	
B-8	Encirclement Sleeve . . . . .	69	
B-9	Encirclement Tee . . . . .	69	
B-10	Encirclement Sleeve and Saddle . . . . .	70	
B-11	Encirclement Saddle . . . . .	70	
Tables			
1	Filler Metal Groups . . . . .	8	
2	Type and Number of Test Specimens for Procedure Qualification Test . . . . .	10	
3	Type and Number of Butt-weld Test Specimens per Welder for Welder Qualification Test and Destructive Testing of Production Welds . . . . .	19	08
4	Maximum Dimensions of Undercutting . . . . .	30	
5	Weld Thickness Versus Diameter of ASTM E 747 Wire Type IQI. . . . .	33	
6	Weld Thickness Versus Diameter of ISO Wire Type IQI. . . . .	33	
7	Type and Number of Test Specimens for Procedure Qualification Test (Flash Weld Only) . . . . .	40	
A-1	Initial Allowable Imperfection Size for $P_r = 0.825$ . . . . .	55	07
A-2	Example Acceptance Table. . . . .	55	
A-3	Acceptance Limits for Buried Volumetric Imperfections . . . . .	59	
A-4	Acceptable Limits for Unrepaired Arc Burns. . . . .	59	
B-1	Type and Number of Specimens—In-Service Welding Procedure Qualification Test . . . . .	64	
B-2	Type and Number of Test Specimens for Longitudinal Seam Welds— Welder Qualification Test . . . . .	65	

# Welding of Pipelines and Related Facilities

## 1 General

### 1.1 SCOPE

This standard covers the gas and arc welding of butt, fillet, and socket welds in carbon and low-alloy steel piping used in the compression, pumping, and transmission of crude petroleum, petroleum products, fuel gases, carbon dioxide, nitrogen and, where applicable, covers welding on distribution systems. It applies to both new construction and in-service welding. The welding may be done by a shielded metal-arc welding, submerged arc welding, gas tungsten-arc welding, gas metal-arc welding, flux-cored arc welding, plasma arc welding, oxyacetylene welding, or flash butt welding process or by a combination of these processes using a manual, semi-automatic, mechanized, or automatic welding technique or a combination of these techniques. The welds may be produced by position or roll welding or by a combination of position and roll welding.

This standard also covers the procedures for radiographic, magnetic particle, liquid penetrant, and ultrasonic testing, as well as the acceptance standards to be applied to production welds tested to destruction or inspected by radiographic, magnetic particle, liquid penetrant, ultrasonic, and visual testing methods.

The values stated in either inch-pound units or SI units are to be regarded separately as standard. Each system is to be used independently of the other, without combining values in any way.

Processes other than those described above will be considered for inclusion in this standard. Persons who wish to have other processes included shall submit, as a minimum, the following information for the committee's consideration:

- a. A description of the welding process.
- b. A proposal on the essential variables.
- c. A welding procedure specification.
- d. Weld inspection methods.
- e. Types of weld imperfections and their proposed acceptance limits.
- f. Repair procedures.

It is intended that all work performed in accordance with this standard shall meet or exceed the requirements of this standard.

## 2 Referenced Publications

The following standards, codes, and specifications are cited in this standard:

API

Spec 5L *Specification for Line Pipe*

RP 2201 *Safe Hot Tapping Practices in the Petroleum & Petrochemical Industries*

ASNT<sup>1</sup>

RP SNT-TC-1A *Personnel Qualification and Certification in Nondestructive Testing*

ACCP *ASNT Central Certification Program*

ASTM<sup>2</sup>

E 164 *Standard Practice for Ultrasonic Contact Examination of Weldments*

E 165 *Standard Test Methods for Liquid Penetrant Examination*

E 709 *Standard Guide for Magnetic Particle Examination*

E 747 *Standard Practice for Design, Manufacture and Material Grouping Classification of Wire Image Quality Indicators (IQI) Used for Radiology*

AWS<sup>3</sup>

A3.0 *Welding, Terms and Definitions*

A5.1 *Covered Carbon Steel Arc Welding Electrodes*

A5.2 *Iron and Steel Oxyfuel Gas Welding Rods*

A5.5 *Low Alloy Steel Covered Arc Welding Electrodes*

A5.17 *Carbon Steel Electrodes and Fluxes for Submerged Arc Welding*

A5.18 *Carbon Steel Filler Metals for Gas Shielded Arc Welding*

A5.20 *Carbon Steel Electrodes for Flux Cored Arc Welding*

A5.28 *Low Alloy Steel Filler Metals for Gas Shielded Arc Welding*

A5.29 *Low Alloy Steel Electrodes for Flux Cored Arc Welding*

BSI<sup>4</sup>

BS 7448:  
Pt. 2 *Fracture Mechanics Toughness Tests Part 2, Method for Determination of  $K_{Ic}$  Critical*

<sup>1</sup>American Society for Nondestructive Testing, Inc., 1711 Arlington Lane, P.O. Box 28518, Columbus, Ohio 43228-0518. [www.asnt.org](http://www.asnt.org)

<sup>2</sup>American Society for Testing and Materials, P.O. Box C700, 100 Barr Harbor Drive, West Conshohocken, Pennsylvania 19428-2959. [www.astm.org](http://www.astm.org)

<sup>3</sup>American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126. [www.aws.org](http://www.aws.org)

<sup>4</sup>BSI, British Standards HQ, 389 Chiswick High Road, London, W4 4AL, United Kingdom. [www.bsi-global.com](http://www.bsi-global.com)

*CTOD and Critical J Values of Welds in Metallic Materials*

ISO<sup>5</sup>

ISO 1027 *Radiographic image quality indicators for non-destructive testing—Principles and Identification*

NACE<sup>6</sup>

MR0175 *Sulfide Stress Cracking Resistant Metallic Materials for Oil Field Equipment*

### 3 Definition of Terms

#### 3.1 GENERAL

The welding terms used in this standard are as defined in AWS A3.0, with the additions and modifications given in 3.2.

#### 3.2 DEFINITIONS

**3.2.1 automatic welding:** Arc welding with equipment that performs the entire welding operation without manual manipulation of the arc or electrode other than guiding or tracking and without a manual welding-skill requirement of the operator.

**3.2.2 branch weld:** The completed groove and/or fillet weld joining a set on or set in branch pipe or a set on or set in branch fitting to a run pipe.

**3.2.3 company:** The owner company or the engineering agency in charge of construction. The company may act through an inspector or another authorized representative.

**3.2.4 contractor:** Includes the primary contractor and any subcontractors engaged in work covered by this standard.

**3.2.5 defect:** An imperfection of sufficient magnitude to warrant rejection based on the stipulations in this standard.

**3.2.6 imperfection:** A discontinuity or irregularity that is detectable by methods outlined in this standard.

**3.2.7 indication:** Evidence obtained by nondestructive testing.

**3.2.8 internal concavity:** A bead that is properly fused to and completely penetrates the pipe wall thickness along both sides of the bevel, but whose center is somewhat below the inside surface of the pipe wall. The magnitude of concavity is the perpendicular distance between an axial extension of

the pipe wall surface and the lowest point on the weld bead surface.

**3.2.9 mechanized welding:** A process where parameters and torch guidance are controlled mechanically or electronically but may be manually varied during welding to maintain the specified welding conditions.

**3.2.10 position welding:** Welding in which the pipe or assembly is not rotating while the weld is being deposited.

**3.2.11 qualified welder:** A welder who has demonstrated the ability to produce welds that meet the requirements of Sections 5 or 6.

**3.2.12 qualified welding procedure:** A tested and proven detailed method by which sound welds with suitable mechanical properties can be produced.

**3.2.13 radiographer:** A person who performs radiographic operations.

**3.2.14 repair:** Any rework on a completed weld that requires welding to correct a fault in the weld that has been discovered by visual or nondestructive testing and is beyond this standard's limits of acceptability.

**3.2.15 roll welding:** Welding in which the pipe or assembly is rotated while the weld metal is being deposited at or near the top center.

**3.2.16 root bead:** The first or stringer bead that initially joins two sections of pipe, a section of pipe to a fitting, or two fittings.

**3.2.17 semiautomatic welding:** Arc welding with equipment that controls only the filler-metal feed. The advance of the welding is manually controlled.

**3.2.18 shall:** Term that indicates a mandatory requirement. The term should indicate a recommended practice.

**3.2.19 weld:** The completed weld joining two sections of pipe, a section of pipe to a fitting, or two fittings.

**3.2.20 welder:** A person who makes a weld.

## 4 Specifications

### 4.1 EQUIPMENT

Welding equipment, both gas and arc, shall be of a size and type suitable for the work and shall be maintained in a condition that ensures acceptable welds, continuity of operation, and safety of personnel. Arc-welding equipment shall be operated within the amperage and voltage ranges given in the qualified welding procedure. Gas-welding equipment shall be operated with the flame characteristics and tip sizes given in the qualified welding procedure. Equipment that does not meet these requirements shall be repaired or replaced.

<sup>5</sup>International Organization for Standardization (ISO), 1, rue de Varembé, Case postale 56, CH-1211 Geneva 20, Switzerland. www.iso.org

<sup>6</sup>NACE International, 1440 South Creek Drive, Houston, Texas 77084-4906. www.nace.org