

# **Shrinkage and Expansion in Oilwell Cements**

API TECHNICAL REPORT 10TR2  
FIRST EDITION, JULY 1997



# **Shrinkage and Expansion in Oilwell Cements**

**Exploration and Production Department**

API TECHNICAL REPORT 10TR2  
FIRST EDITION, JULY 1997



## SPECIAL NOTES

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

API is not undertaking to meet the duties of employers, manufacturers, or suppliers to warn and properly train and equip their employees, and others exposed, concerning health and safety risks and precautions, nor undertaking their obligations under local, state, or federal laws.

Information concerning safety and health risks and proper precautions with respect to particular materials and conditions should be obtained from the employer, the manufacturer or supplier of that material, or the material safety data sheet.

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. Sometimes a one-time extension of up to two years will be added to this review cycle. This publication will no longer be in effect five years after its publication date as an operative API standard or, where an extension has been granted, upon republication. Status of the publication can be ascertained from the API Authoring Department [telephone (202) 682-8000]. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this standard or comments and questions concerning the procedures under which this standard was developed should be directed in writing to the director of the Authoring Department (shown on the title page of this document), American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

API standards are published to facilitate the broad availability of proven, sound engineering and operating practices. These standards are not intended to obviate the need for applying sound engineering judgment regarding when and where these standards should be utilized. The formulation and publication of API standards is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

*All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.*

## FOREWORD

Dimensional change after placement in oil and gas well cements, a phenomenon often referred to as shrinkage, has often been used to explain various problems (e.g., microannulus leading to bad cement bond logs, interzonal communication leading to costly remedial jobs and also lack of a seal to the gas of cement inflatable packers). Attempts have been made to find additives to decrease shrinkage, but it seems that shrinkage (as well as the exothermal reaction) are closely related to the hydration of the cement. The best solution for this shrinkage so far has been the identification of additives that favor the expansion of the cement. However, even if cement expands dimensionally, it still will shrink internally. In this case, the bulk expansion of the cement sample is simply superposed on an inner shrinkage that will affect the porosity of the sample. Shrinkage is not just one property of cement, such as rheology or thickening time that can be defined by one measurement. This is probably why little consensus has been reached today in the industry on this important issue, in spite of a large amount of work devoted to the subject.

In 1994, API proposed to open a work group on shrinkage. This report is an attempt to bring more understanding to this important area of cementing. One of the objectives of the work group was also to propose equipment to investigate shrinkage and expansion in oilwell cements. This report will address the objectives of that task group, which were:

- To develop standardized test procedures to measure expansion/shrinkage.
- To investigate possible impacts on invasion of wellbore fluids (gas, water).
- To standardize definitions of terms for cement hydration.

This report is a summary of all the background information and actual data that were generated to meet the objectives outlined above.

The equipment described in the report is the minimum recommended to measure the parameters in question.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any federal, state, or municipal regulation with which this publication may conflict.

Suggested revisions are invited and should be submitted to the director of the Exploration and Production Department, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005.

# CONTENTS

	Page
1 INTRODUCTION.....	1
2 REFERENCES .....	1
3 DEFINITIONS AND SYMBOLS .....	1
3.1 Definitions .....	1
3.2 List of Symbols .....	1
4 DISCUSSION OF SHRINKAGE AND EXPANSION.....	1
4.1 Cause and Results of Shrinkage and Expansion.....	1
5 EXPERIMENTAL PROCEDURE .....	4
5.1 The Annular Expansion Ring: A Measurement of Linear Expansion Under Conditions of Free Access to Water.....	4
5.2 The Cylindrical Sleeve: A Measurement of Bulk Expansion Under Conditions of Free Access to Water .....	4
5.3 The Membrane: A Measurement of Bulk Shrinkage or Bulk Expansion Under Impermeable Conditions .....	7
5.4 The CHA: A Measurement of Inner Shrinkage Under Free Access to Gas.....	7
6 DATA ANALYSIS .....	14
6.1 Annular Ring and Linear Bar .....	14
6.2 Sleeve and Membrane Tests .....	14
6.3 CHA Tests .....	15
7 RESULTS INTERPRETATION .....	15
7.1 General Comments About the Expansion.....	15
7.2 Neat Slurries .....	15
7.3 Influence of Foaming Agent and Entrapped Air.....	16
7.4 Conclusion.....	16
7.5 Action of an Expanding Agent .....	16
7.6 Porosity Effect .....	16
7.7 Research of Possible Trends .....	17
8 CONCLUSION .....	17
APPENDIX A—SUGGESTED REFERENCES.....	51
Figures	
1 Cement Hydration .....	3
2 The Annular Expansion Mold .....	5
3 Measurement of Cement Expansion .....	6
4 Measurement of Cement Shrinkage (or Expansion).....	8
5 Experiment 1 .....	9
6 Experiment 2 .....	11
7 Experiment 3 .....	12
8 Cement Hydration Analyzer .....	13
9 CHA: Shrinkage Measurement—Test G4.....	38
10 CHA: Shrinkage Measurement—Test P3 .....	39
11 Action of Expansion Agent—Expansion as a Function of Shrinkage .....	40

	Page
12 Porosity and Membrane Shrinkage . . . . .	41
13 Porosity and Membrane Shrinkage . . . . .	42
14 Action of Expanding Agent, Latex, and Dispersant . . . . .	43
15 Cement Volume/Total Volume Ratio and Membrane Shrinkage . . . . .	44
16 Cement Volume/Total Volume Ratio and Membrane Shrinkage . . . . .	45
17 Water Weight/Cement Weight Ratio and Membrane Shrinkage. . . . .	46
18 Water Weight/Cement Weight Ratio and Membrane Shrinkage. . . . .	47
19 Water Weight/Cement Weight Ratio and Membrane Shrinkage. . . . .	48
20 CHA Test, System 1. . . . .	49
21 CHA Test, System 2. . . . .	50

Tables

1 General Table . . . . .	18
2 Neat Slurry (H) Test, 16.8 ppg. . . . .	19
3 Neat Slurry (A) Test, 15.6 ppg. . . . .	20
4 Foaming Agent Test, 16.8 ppg. . . . .	21
5 Foaming Agent Test, 16.8 ppg. . . . .	22
6 Expanding Agent Test, 17.1 ppg . . . . .	23
7 10 Percent Expanding Test, 17.5 ppg . . . . .	24
8 5 Percent Latex Slurry Test, 16.8 ppg . . . . .	25
9 10 Percent Latex Slurry Test, 16.8 ppg . . . . .	26
10 10 Percent Latex Slurry Test, 16.8 ppg . . . . .	27
11 5 Percent Expanding Plus Latex Test, 17.1 ppg . . . . .	28
12 5 Percent CaO:MgO + Latex (5 Percent) + Dispersant (1 Percent) Test, 17.1 ppg. . . . .	29
13 10 Percent CaO:MgO + Latex (5 Percent) + Dispersant (1 Percent) Test, 17.5 ppg. . . . .	30
14 Proprietary Blend Test, 16.2 ppg . . . . .	31
15 Proprietary Blend Test, 16.2 ppg . . . . .	32
16 Amoco Latex Test, 23.0 ppg . . . . .	33
17 Slag Mix Test, 13.0 ppg. . . . .	34
18 Slag Mix Test, 14.6 ppg. . . . .	35
19 Neat H Slurries, 16.8 ppg . . . . .	36
20 Neat Holnam H Slurries. . . . .	36
21 The Dispersion Effect On a Neat Slurry . . . . .	37
22 Microcement . . . . .	37

# Shrinkage and Expansion in Oilwell Cements

## 1 Introduction

A flawless cementation of the casing strings is fundamental not only for safety reasons, but also to keep drilling and production costs at a minimum level.

A cement job has to fulfill multiple conditions, but its main function is to prevent fluid and gas flow through the annulus by ensuring an impermeable bond and exhibiting sufficient compressive and shear bond strength.

Various factors can affect the sealing, such as poor mud removal, as well as bad slurry properties and borehole conditions. It is also recognized that the volumetric changes of cement during hydration substantially contribute to these problems. Bulk and inner volume changes produce bonding and permeability changes, respectively.

In this work, volume changes were better understood by measuring them on different slurries. Three different setups that correspond to three different testing conditions were used.

## 2 References

A list of suggested references may be found in Appendix A.

## 3 Definitions and Symbols

### 3.1 DEFINITIONS

For the purposes of this report, the following definitions apply:

**3.1.1 cement:** when the word is used alone, it refers to the material in any of the states from cement slurry to hard cement.

**3.1.2 cement slurry:** a mixture of Portland cement, water, and additives at a consistency below 50 Bc.

**3.1.3 gel cement:** cement slurry between the time at 50 Bc and the time at which the transit time of ultrasonic compressional P waves starts to decrease (UCA equipment).

**3.1.4 gel cement under plastic state:** a gel cement that can still deform to match the shape of its container.

**3.1.5 hard cement:** a material where the transit time of ultrasonic compressional P waves has decreased compared to the initial base line.

**3.1.6 Portland cement:** the powder as received from the supplier.

### 3.2 LIST OF SYMBOLS

The following symbols are used in this report:

- $V_i$  = initial volume of cement
- $V_f$  = final volume of cement
- $T$  = temperature of the cement

- $P$  = pore pressure inside the cement
- $M_t$  = micrometer measurement after curing
- $M_i$  = initial micrometer measurement
- $\%Lex$  = defined by equation [1], linear expansion measured with the annular ring
- $V_i$  = initial volume of the sleeve
- $V_f$  = final volume of the sleeve
- $\%Bex$  = defined by equation [3], bulk expansion measured with the sleeve
- $D_i$  = 1.65 inches (initial diameter of the sleeve)
- $D_f$  = final diameter of the sleeve
- $C_i$  = initial circumference of the sleeve
- $C_f$  = final circumference of the sleeve
- $h$  = height of the sleeve
- $\Delta C_{12}$  = difference between  $C_{12}$  final and  $C_{12}$  initial
- $\%Bch$  = defined by equation [4], bulk volume change measured with the membrane
- $V_p$  = volume compensated by the piston movement
- $V_g$  = volume of gas entered in the slurry
- $V_i$  = 392.5 cm<sup>3</sup> (estimated by filling up the cell with water)
- $\%Ish$  = defined by equation [5], inner shrinkage measured with the CHA

## 4 Discussion of Shrinkage and Expansion

### 4.1 CAUSE AND RESULTS OF SHRINKAGE AND EXPANSION

Shrinkage and expansion in cement result from the formation of hydration products having a different density from the compounded density of the reaction components. This can result in:

- a. Change in pore volume.
- b. Change in pore pressure.
- c. Change in sample dimensions.
- d. Change in internal stress.

The change in sample dimensions will be referred to as bulk shrinkage or bulk expansion. The change in pore volume will be referred to as inner shrinkage.

Shrinkage and expansion of cement refer to the result of the measurement of a volume change in cement. This will be expressed in percent by volume. The volume to which all volume changes are related, is the volume of the slurry immediately after mixing and placement in the experimental equipment. The general expression for shrinkage and expansion is: