

Casing and Tubing

API SPECIFICATION 5CT
ELEVENTH EDITION, DECEMBER 2023

API MONOGRAM PROGRAM EFFECTIVE DATE:
JANUARY 1, 2025

ERRATA 1, MAY 2024



American
Petroleum
Institute

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to ensure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Copyright © 2023 American Petroleum Institute

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, “can” denotes a statement of possibility or capability.

In the interests of worldwide application of this standard, the API Subcommittee on Tubular Goods (SC5) has decided, after detailed technical analysis, that certain documents listed in Section 2 and prepared by API SC5 or other technical committees are interchangeable in the context of the relevant requirement with the relevant document prepared by the International Organization for Standardization or the ASTM International. These latter documents are cited in the running text following the API reference and preceded by “or,” for example, “API XXXX or ISO YYYY” or “ISO YYYY or ASTM ZZZZ.” Application of an alternative document cited in this manner may lead to technical results different from the use of the preceding API reference. However, both results are acceptable, and these documents are thus considered interchangeable in practice.

In this standard, data are expressed in both the International System of Units (SI) and the United States customary (USC) units. For a specific order item, it is intended that only one system of units be used, without combining data expressed in the other system. Products manufactured to specifications expressed in either of these unit systems shall be considered equivalent and totally interchangeable. Consequently, conformance with the requirements of this standard as expressed in one system provides conformance with requirements expressed in the other system. In the text, data in SI units are followed by data in USC units in parentheses.

See Annex A of API Specification Q1 or the API website for information pertaining to the API Monogram Program and use of the API Monogram on applicable products, or for information about the Monogram licensing program, please contact certification@api.org.

For API Monogram Program licensees and APIQR program registrants, this edition and any normative references (see Section 2) shall become effective on the program date printed on the cover but may be used voluntarily from the date of publication.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every 5 years. A one-time extension of up to 2 years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001, standards@api.org.

Contents

1	Scope	1
1.1	Coverage	1
1.2	Applicability—Connections	1
1.3	Applicability—Grades	1
1.4	Supplementary Requirements	2
1.5	Eligibility for Licensed/Registered Industry Mark	2
2	Normative References	2
3	Terms, Definitions, Symbols, Acronyms, and Abbreviations	4
3.1	Terms and Definitions	4
3.2	Symbols	9
3.3	Acronyms and Abbreviations	9
4	Information to Be Supplied by the Purchaser	10
4.1	Ordering Products According to This Standard	10
4.2	Casing	10
4.3	Tubing	13
4.4	Coupling Stock, Coupling Material, and Accessory Material	15
5	Process of Manufacture	17
5.1	General	17
5.2	Heat Treatment	17
5.3	Straightening	18
5.4	Traceability	19
5.5	Processes Requiring Validation	19
6	Material Requirements	20
6.1	Chemical Composition	20
6.2	Tensile Properties	20
6.3	Charpy V-notch Test—General Requirements	21
6.4	Charpy V-notch—Absorbed Energy Requirements for Coupling Stock, Coupling Material, Coupling Blanks, and Couplings	22
6.5	Charpy V-notch—Absorbed Energy Requirements for Pipe	23
6.6	Charpy V-notch—Absorbed Energy Requirements for Accessory Material	24
6.7	Maximum Hardness	24
6.8	Hardness Variation—Grades C90, T95, C110, and Q125	25
6.9	Process Control—Grades C90, T95, C110, and Q125	25
6.10	Hardenability—Minimum Percentage Martensite for Quenched and Tempered Products	25
6.11	Grain Size—Grades C90, T95, and C110	27
6.12	Surface Condition—Grades L80 9Cr and L80 13Cr	27
6.13	Flattening—Electric-welded Pipe	27
6.14	Sulfide Stress Cracking Test—Grades C90, T95, and C110	28
7	Dimensions, Masses, Tolerances, Product Ends, and Defects	30
7.1	Labels and Sizes	30
7.2	Dimensions and Masses	30
7.3	Diameter	31
7.4	Wall Thickness	31
7.5	Mass	32
7.6	Length	32
7.7	Casing Joints	32
7.8	Height and Trim of Electric-weld Flash	32
7.9	Straightness	33

7.10	Drift Requirements.....	34
7.11	Tolerances on Dimensions and Masses.....	34
7.12	Product Ends.....	35
7.13	Defects.....	36
7.14	Coupling Make-up and Thread Protection.....	37
8	Couplings.....	38
8.1	General Requirements.....	38
8.2	Alternative Grades or Heat Treatments.....	38
8.3	Mechanical Properties.....	39
8.4	Dimensions and Tolerances.....	39
8.5	Regular Couplings.....	39
8.6	Special Clearance Couplings—All Grades Except Q125.....	39
8.7	Combination Couplings.....	40
8.8	Seal-ring Couplings.....	40
8.9	Special Bevel Tubing Regular Couplings—All Grades Except C110 and Q125.....	40
8.10	Threading.....	40
8.11	Surface Inspection.....	40
8.12	Measurement of Imperfections.....	41
8.13	Repair and Removal of Imperfections and Defects.....	41
8.14	Thread Surface Treatment—Grade Q125.....	42
8.15	Couplings and Coupling Blank Protection—Grades C90, T95, C110, and Q125.....	42
9	Inspection and Testing.....	42
9.1	Test Equipment.....	42
9.2	Lot Definition for Testing of Mechanical Properties.....	42
9.3	Testing of Chemical Composition.....	43
9.4	Tensile Tests.....	44
9.5	Flattening Test.....	46
9.6	Hardness Test.....	48
9.7	Impact Test.....	54
9.8	Grain Size Determination—Grades C90, T95, and C110.....	56
9.9	Hardenability—Grades C90, T95, and C110.....	56
9.10	Sulfide Stress Cracking Test—Grades C90, T95, and C110.....	56
9.11	Metallographic Evaluation—EW Grades J55, K55, N80, L80 Type 1, R95, P110, and Q125... ..	59
9.12	Hydrostatic Tests.....	60
9.13	Dimensional Testing.....	62
9.14	Visual Inspection.....	66
9.15	Nondestructive Examination.....	68
10	Marking.....	76
10.1	General.....	76
10.2	Stamp Marking Requirements.....	77
10.3	Stencil Marking Requirements.....	79
10.4	Color Identification.....	79
10.5	Thread and End-finish Marking.....	80
10.6	Pipe-threader Marking Requirements.....	81
11	Coating and Protection.....	81
11.1	Coatings.....	81
11.2	Thread Protectors.....	82
12	Documents.....	83
12.1	Electronic Media.....	83
12.2	Certification Requirements.....	83

12.3	Certification Content.....	83
12.4	Retention of Records.....	84
13	Minimum Facility Requirements for Various Categories of the Manufacturer	84
13.1	Pipe Mill.....	84
13.2	Processor.....	85
13.3	Pipe Threader	85
13.4	Coupling, Pup Joint, or Accessory Manufacturer	85
Annex A (normative) Supplementary Requirements		87
Annex B (normative) Purchaser Inspection.....		99
Annex C (normative) Tables in SI Units		100
Annex D (normative) Figures in SI (USC) Units.....		148
Annex E (normative) Tables in USC Units		171
Annex F (normative) Requirements for Thread Protector Design and Validation.....		220
Annex G (informative) Procedures Used to Convert from USC Units to SI Units.....		225
Bibliography		236

Figures

D.1	Short Round Thread Casing and Coupling	148
D.2	Long Round Thread Casing and Coupling.....	148
D.3	Buttress Thread Casing and Coupling	149
D.4	Non-upset Tubing and Coupling	150
D.5	External Upset Tubing and Coupling.....	151
D.6	Rounded Nose for External Upset Tubing.....	152
D.7	Integral-joint Tubing	152
D.8	Tensile Test Specimens	153
D.9	Example Location of Test Samples Removed from Product	154
D.10	Through-wall Hardness Test.....	155
D.11	Impact Test Specimen Orientation.....	156
D.12	Charpy Specimen Dimensions	156
D.13	Measuring Full-length Straightness.....	157
D.14	Measuring End Straightness	157
D.15	Gag Straightening Fiber Strain Factors.....	158
D.16	Upset-end Hook Measurement	158
D.17	Examples of Marking Requirements and Sequence for Manufacturers and Threaders Using Section 10 and Table C.43 or Table E.43	159
D.18	Reference Indicators.....	162
D.19	SR 13.1 Seal-ring Coupling and Nonmetallic Ring for Round Thread Casing.....	164
D.20	SR 13.2 Seal-ring Coupling and Nonmetallic Ring for Buttress Thread Casing	165
D.21	SR 13.3 Seal-ring Coupling and Nonmetallic Ring for Non-upset Tubing	166
D.22	SR 13.4-Seal-ring Coupling and Nonmetallic Ring for Upset Tubing	167
D.23	Example of a 90° Hook-type Tool	168
D.24	Axial Impact Test Apparatus.....	169
D.25	45° Impact Test Apparatus.....	169
D.26	Stripping Test Apparatus	170
D.27	Seal-ring Paint Band Example	170
D.28	Location of Hardness Impressions on DCB Specimen.....	170

Tables

1	Purchaser-supplied Information (Casing)	10
2	Optional Requirements Specified by the Purchaser (Casing)	11
3	Purchaser/Manufacturer Agreement (Casing)	12
4	Purchaser-supplied Information (Tubing)	13
5	Optional Requirements Specified by the Purchaser (Tubing).....	14
6	Purchaser/Manufacturer Agreement (Tubing)	15
7	Purchaser-supplied Information (Coupling Stock and Coupling Material and Accessory Material)	16
8	Optional Requirements Specified by the Purchaser (Coupling Stock and Coupling Material and Accessory Material)	16
9	Full-size Test Specimen Minimum Absorbed Energy Requirements (Grades N80, R95, L80, C90, T95, P110, C110, and Q125).....	22
10	Full-size Test Specimen Minimum Absorbed Energy Requirements (Grades N80, R95, L80, C90, T95, and P110)	23
11	Full-size Test Specimen Minimum Absorbed Energy Requirements (Grades C110 and Q125)..	23
12	NACE Method A Requirements for Tensile Test Specimens.....	29
13	NACE Method D Requirements for Standard Specimens.....	29
14	Electric-weld Flash Height and Trim (All Grades Except P110 and Q125).....	33
15	Dimension Tolerances (Pipe OD)	34
16	Dimension Tolerances (Upset Integral Tubing)	34
17	Dimension Tolerances (External Upset Tubing).....	35
18	Standard Mass Tolerances	35
19	Arm Displacement Values and Max/Min Tolerances	59
20	Stamp Marking	78
A.1	Supplementary Requirements Applicable to Couplings.....	87
A.2	(SR 12) Inspection Lot Sample Sizes vs <i>F</i> Factor.....	91
A.3	(SR 12) Probability of Defective Product.....	92
C.1	API Casing List (Sizes, Masses, Wall Thickness, Grade, and Applicable End-finish)	100
C.2	API Tubing List (Sizes, Masses, Wall Thickness, Grade, and Applicable End-finish)	103
C.3	Process of Manufacture and Heat Treatment	104
C.4	Chemical Composition, Mass Fraction (%)	105
C.5	Tensile and Hardness Requirements	106
C.6	Elongation Table	107
C.7	Critical Thickness for Couplings with API Threads	109
C.8	Acceptable Size Impact Specimens and Absorbed Energy Reduction Factor.....	109
C.9	Hierarchy of Test Specimen Orientation and Size.....	110
C.10	Transverse Impact Specimen Size Required	110
C.11	Longitudinal Impact Specimen Size Required	111
C.12	Minimum Absorbed Energy for Couplings, Coupling Stock, Coupling Material, and Coupling Blanks—Transverse Orientation (Joules).....	112
C.13	Minimum Absorbed Energy for Couplings, Coupling Stock, Coupling Material, and Coupling Blanks—Longitudinal Orientation (Joules)	112
C.14	Minimum Absorbed Energy for Pipe—Transverse Orientation (Joules).....	113
C.15	Minimum Absorbed Energy for Pipe—Longitudinal Orientation (Joules)	113
C.16	Frequency of Charpy V-notch Testing—Pipe, Coupling Stock, Coupling Material, Coupling Blanks, Couplings, and Accessory Material.....	114
C.17	Distance between Plates for Electric-weld Flattening Tests	115
C.18	Dimensions and Masses for Standard Casing and for Casing Threaded with API Round Thread and Buttress Thread	116
C.19	Dimensions and Masses for Standard Tubing and for Tubing Threaded with API Non-upset, External Upset, and Integral Tubing Connections.....	121
C.20	External Upset Tubing Dimensions for API Connections for Grades H40, J55, L80, R95, N80, C90, T95, and P110	124

C.21	Integral Tubing Connection Dimensions for API Connections for Grades H40, J55, L80, R95, N80, C90, and T95.....	125
C.22	Range Lengths	126
C.23	Standard Drift Size	126
C.24	Alternative Drift Size	127
C.25	Maximum Permissible Depth of Linear Imperfections	127
C.26	Upset Products—Maximum Permissible Depth of Imperfections	128
C.27	API Round Thread Casing Coupling—Dimensions, Tolerances, and Masses	129
C.28	API Buttress Thread Casing Coupling—Dimensions, Tolerances, and Masses	130
C.29	API Non-upset Tubing Coupling—Dimensions, Tolerances, and Masses	131
C.30	API External Upset Tubing Coupling—Dimensions, Tolerances, and Masses	131
C.31	Permissible Depth of External Imperfections on Coupling	132
C.32	Frequency of Tensile Tests—Casing and Tubing	133
C.33	Frequency of Tensile Tests—Coupling Stock, Coupling Material, and Coupling Blanks ..	134
C.34	Frequency of Tensile Testing—Pup Joints and Accessory Material.....	135
C.35	Frequency of Hardness Testing	136
C.36	Frequency of Flattening Tests	138
C.37	Summary of NDE Methods for Seamless Pipe, Coupling Stock, Body of Welded Pipe, and Accessory Material (in Accordance with 9.15.9 and 9.15.11).....	139
C.38	Acceptance (Inspection) Levels	140
C.39	Artificial Reference Indicators	141
C.40	Size of Stamp Markings.....	141
C.41	Grade Color Codes	142
C.42	Thread Type Markings	142
C.43	Marking Requirements and Sequence.....	143
C.44	Retention of Records.....	147
E.1	API Casing List (Sizes, Masses, Wall Thickness, Grade, and Applicable End-finish).....	171
E.2	API Tubing List (Sizes, Masses, Wall Thickness, Grade, and Applicable End-finish).....	174
E.3	Process of Manufacture and Heat Treatment	175
E.4	Chemical Composition, Mass Fraction (%)	176
E.5	Tensile and Hardness Requirements.....	177
E.6	Elongation Table	178
E.7	Critical Thickness for Couplings with API Threads	181
E.8	Acceptable Size Impact Specimens and Absorbed Energy Reduction Factor.....	182
E.9	Hierarchy of Test Specimen Orientation and Size.....	182
E.10	Transverse Impact Specimen Size Required	182
E.11	Longitudinal Impact Specimen Size Required.....	183
E.12	Minimum Absorbed Energy for Couplings, Coupling Stock, Coupling Material, and Coupling Blanks—Transverse Orientation (ft·lb)	184
E.13	Minimum Absorbed Energy for Couplings, Coupling Stock, Coupling Material, and Coupling Blanks—Longitudinal Orientation (ft·lb).....	184
E.14	Minimum Absorbed Energy for Pipe—Transverse Orientation (ft·lb)	185
E.15	Minimum Absorbed Energy for Pipe—Longitudinal Orientation (ft·lb).....	185
E.16	Frequency of Charpy V-notch Testing—Pipe, Coupling Stock, Coupling Material, Coupling Blanks, Couplings, and Accessory Material.....	186
E.17	Distance between Plates for Electric-weld Flattening Tests	187
E.18	Dimensions and Masses for Standard Casing and for Casing Threaded with API Round Thread and Buttress Thread	188
E.19	Dimensions and Masses for Standard Tubing and for Tubing Threaded with API Non-upset, External Upset, and Integral Tubing Connections.....	193
E.20	External Upset Tubing Dimensions for API Connections for Grades H40, J55, L80, R95, N80, C90, T95, and P110	196
E.21	Integral Tubing Connection Dimensions for API Connections for Grades H40, J55, L80, R95, N80, C90, and T95.....	197

E.22	Range Lengths	198
E.23	Standard Drift Size	198
E.24	Alternative Drift Size	199
E.25	Maximum Permissible Depth of Linear Imperfections	199
E.26	Upset Products—Maximum Permissible Depth of Imperfections	200
E.27	API Round Thread Casing Coupling—Dimensions, Tolerances, and Masses	201
E.28	API Buttress Thread Casing Coupling—Dimensions, Tolerances, and Masses	202
E.29	API Non-upset Tubing Coupling—Dimensions, Tolerances, and Masses	203
E.30	API External Upset Tubing Coupling—Dimensions, Tolerances, and Masses	204
E.31	Permissible Depth of External Imperfections on Coupling	204
E.32	Frequency of Tensile Tests—Casing and Tubing	205
E.33	Frequency of Tensile Tests—Coupling Stock, Coupling Material, and Coupling Blanks.....	206
E.34	Frequency of Tensile Testing—Pup Joints and Accessory Material.....	207
E.35	Frequency of Hardness Testing	208
E.36	Frequency of Flattening Tests	210
E.37	Summary of NDE Methods for Seamless Pipe, Coupling Stock, Body of Welded Pipe, and Accessory Material (in Accordance with 9.15.9 and 9.15.11).....	211
E.38	Acceptance (Inspection) Levels	212
E.39	Artificial Reference Indicators	213
E.40	Size of Stamp Markings.....	213
E.41	Grade Color Codes	214
E.42	Thread Type Markings	214
E.43	Marking Requirements and Sequence.....	215
E.44	Retention of Records.....	219
F.1	Class A: Axial Impact Test Using 38 mm (1.5 in.) Diameter Steel Bar.....	222
F.2	Class B: Axial Impact Test Using 38 mm (1.5 in.) Diameter Steel Bar.....	222
F.3	Class A: Angular (45°) Impact Test Using a Flat Steel Plate	223
F.4	Class B: Angular (45°) Impact Test Using a Flat Steel Plate	223
G.1	Drift Constants	227

Casing and Tubing

1 Scope

1.1 Coverage

This standard specifies the technical delivery conditions for steel pipes (casing, tubing, and pup joints), coupling stock, coupling material, and accessory material.

For products covered by this standard, the sizes, masses, and wall thicknesses, as well as grades and applicable end-finishes, are provided. API 5L pipe may be ordered as casing in accordance with API 5C6.

By agreement between the purchaser and the manufacturer, this standard can also be applied to other plain-end pipe sizes and wall thicknesses.

1.2 Applicability—Connections

This standard is applicable to the following connections in accordance with API 5B:

- short round thread casing (SC);
- long round thread casing (LC);
- buttress thread casing (BC);
- non-upset tubing (NU);
- external upset tubing (EU);
- integral tubing (IJ).

For such connections, this standard specifies the technical delivery conditions for couplings and thread protection. Supplementary requirements (SRs) that can optionally be agreed upon for enhanced leak resistance connections (LC) are provided.

This standard also can be applied to products with connections not covered by API standards.

This standard is not applicable to threading requirements.

NOTE Dimensional requirements on threads and thread gauges, stipulations on gauging practice, gauge specifications, and instruments and methods for inspection of threads are given in API 5B.

1.3 Applicability—Grades

The products to which this standard is applicable include the following grades: H40, J55, K55, N80 (all types), L80 (all types), C90, R95, T95, P110, C110, and Q125. In this standard, when the symbol L80 is used alone, it is applicable to Grades L80 Type 1, L80 3Cr, L80 9Cr, and L80 13Cr; when the symbol N80 is used alone, it is applicable to Grades N80 Type 1 and N80Q.

Caution—Any sulfide stress cracking (SSC) test performed as part of this standard is for quality control purposes only and does not qualify the material for any specific sour service application. NACE MR0175/ISO 15156 provides guidelines for material selection in H₂S (sour) service environment for resistance to cracking; however, grades are not necessarily immune to cracking under all service conditions. It is the product user's responsibility to ensure that the product is suitable for the intended application with consideration of all environmental degradation threats during both normal operation and system upsets.