



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS3688™</b>	<b>REV. B</b>
	Issued 1974-03 Revised 1988-10 Reaffirmed 2022-08	
Superseding AMS3688A		
Adhesive, Foaming, Honeycomb Core Splice, Structural -55 to +82 °C (-65 to +180 °F)		

RATIONALE

AMS3688B has been reaffirmed to comply with the SAE Five-Year Review policy.

**1. SCOPE:**

**1.1 Form** This specification covers a foaming-type, heat-curing, resin-base adhesive in the form of paste or sheet.

**1.2 Application:** Primarily for use in splicing aluminum alloy or nonmetallic honeycomb core and for providing a shear tie between core edges and inserts or edge members in honeycomb assemblies for use over the range -55° to +82°C (-65° to +180°F). It is useful for filling gaps between core faces which are inserted into channels or similar areas where bonding pressure cannot be obtained.

**1.3 Safety - Hazardous Materials:** While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

**2. APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:** Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

**AMS 2350 - Standards and Test Methods**

**AMS 2825 - Material Safety Data Sheets**

**AMS 4037 - Aluminum Alloy Sheet and Plate, 4.4Cu - 1.5Mg - 0.60Mn  
(2024-T3 Flat Sheet, -T351 Plate)**

**AMS 4348 - Honeycomb Core, Aluminum Alloy, Corrosion Inhibited, for  
Sandwich Construction, 5052, 350 (175)**

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/content/AMS3688B/>